

L12 ANSWER 5 OF 19 CAPLUS COPYRIGHT 2005 ACS on STN

ACCESSION NUMBER: 1991:687240 CAPLUS

DOCUMENT NUMBER: 115:287240

TITLE: Controlled-release tablets coated with compositions containing water-soluble and water-insoluble polymers  
INVENTOR(S): Hirashima, Naoki; Kashiwabara, Toshio; Hirai, Shinichiro

PATENT ASSIGNEE(S): Takeda Chemical Industries, Ltd., Japan

SOURCE: Jpn. Kokai Tokkyo Koho, 6 pp.

CODEN: JKXXAF

DOCUMENT TYPE: Patent

LANGUAGE: Japanese

FAMILY ACC. NUM. COUNT: 1

PATENT INFORMATION:

| PATENT NO.             | KIND | DATE     | APPLICATION NO. | DATE     |
|------------------------|------|----------|-----------------|----------|
| JP 03197421            | A2   | 19910828 | JP 1989-338971  | 19891226 |
| PRIORITY APPLN. INFO.: |      |          | JP 1989-338971  | 19891226 |

AB Pharmaceutical-containing controlled-release tablets are coated with compns. containing water-soluble polymers (WS) and water-insol. (WI) polymers (blend weight

ratio WS:WI = 1 : 1-3) of 100-1000  $\mu$ m thickness. Ascorbic acid 250, Na ascorbate 281.23, and diluents 66.37 mg were mixed and granulated, which were mixed with 2.4 mg Mg stearate and pressed to give a tablet. The tablets (300 g) were coated with a solution of 12 g Et cellulose, 8 g polyethylene glycol, and 200 mL EtOH to give film-coated tablets (polyethylene glycol content 40%, film thickness 100  $\mu$ m), which showed vitamin C dissoln. rate of 10.1, 46.3, 78.3, 92.4, and 98.1% after 1, 4, 8, 12, and 18 h, resp., vs. 70.0, 97.0, 99.9, 100, and 100% after 6, 15, 30, 60, and 120 min, resp., for a control prepared similarly but without film-coating. The film-coated tablets had strong mech. strength in wet conditions.

A